

## RED ALDER

SCIENTIFIC NAME: *Alnus rubra*



### DISTRIBUTION AND AVAILABILITY



- Coastal Western North America.

#### COLOR:

##### Range Variation







Red alder tends to be a light tan to reddish brown; color darkens and reddens with age. There is no visible distinction between heartwood and sapwood. Small sound knots and large aggregate rays appear as occasional small streaks on the face grain that are not considered as defects in the wood.



#### DISCLAIMER

A single sample may not accurately represent the full range of natural variations to be expected. Due to the inherent properties and characteristics of wood, these samples should be viewed as an approximation of what can be obtained. Some wood species have more natural variance in appearance than others. We have made every effort to make colors as accurate as possible. Colors on screen may vary depending on your screen setting and resolution.

**RED ALDER INFORMATION**

		28 lbs/ft <sup>3</sup> (450 kg/m <sup>3</sup> )
<b>AVERAGE DRIED WEIGHT</b>		
	GRAIN   TEXTURE	The wood has fairly straight grain, and is fine-grained and even-textured.
	PRICING   AVAILABILITY	Low to Moderate. <i>Readily Available</i>
	COVERED EXTERIOR RATING	<b>Poor</b>   Good   Excellent
	PHOTOSENSITIVITY	High   <b>Moderate</b>   Low
	CONSERVATION STATUS	LC - Least Concern (IUCN 3.1)
	VENEER OPTIONS	Rotary Cut   Flat Cut   Quarter Cut

CONTACT OUR TEAM

**T 604-776-2265**  
2320 Peardonville Road, Abbotsford, BC  
Canada V2T 6J8  
sales@lineaceilings.com [lineaceilings.com](http://lineaceilings.com)

